

TYPICAL PHYSICAL CHARACTERISTICS OF Bitumen 60/70 (JOR)

CHARACTERISTIC	SPECIFICATION	TEST METHOD
Density @ 25 °C	1.01 - 1.06	D – 70 , D – 3289
Penetration @ 25 °C	60 / 70	D – 5
Softening Point °C	49 / 56	D – 36
Ductility @ 25 °C	100 Min	D – 113
Loss On Heating (wt %)	0.2 Max	D – 6
Drop In Penetration After heating - %	20 Max	D – 6 & D – 5
Flash Point °C	250 Min	D – 92
Solubility In CS2 (wt %)	99.05 Min	D – 4
