

REMEL INTERNATIONAL F.Z.E.

TYPICAL PHYSICAL CHARACTERISTICS OF AROMATIC RUBBER PROCESS OIL (BOC)

PHYSICAL PROPERTIES	UNIT	TEST METHOD	AROMATIC R.P.O - SPECIFICATIONS		
			Tire – 245	Tire – 250	Tire – 290
Density @ 15°C	Kg/M ³	ASTM D – 1298	985 – 1000	990 – 1040	985 – 1015
Flash Point (COC)	°C	ASTM D – 92	204	246	216
Kinematics Viscosity @ 100°C	cSt	ASTM D – 445	6 – 12	50 – 80	19 – 28
VGC (Max)	-	ASTM D – 2501	0.97	0.95	0.94
Aniline Point (Min)	°C	ASTM D – 611	24	30	24
