

REMEL INTERNATIONAL F.Z.E.

TYPICAL PHYSICAL CHARACTERISTICS OF PARAFFINIC RUBBER PROCESS OIL (BOC)

PHYSICAL PROPERTIES	UNIT	TEST METHOD	PARAFFINIC R.P.O - SPECIFICATIONS	
			Tire – 840	Tire – 845
Density @ 15°C	Kg/M ³	ASTM D – 1298	895	905
Flash Point (COC)	°C	ASTM D – 92	174	183
Kinematics Viscosity @ 40°C	cSt	ASTM D – 445	21 – 28	26 – 42
Kinematics Viscosity @ 100°C			4.2 – 6	5 – 7
VGC	-	ASTM D – 2501	0.84	0.85
Aniline Point	°C	ASTM D – 611	92	82
