

TYPICAL PHYSICAL CHARACTERISTICS OF RUBBER PROCESS OIL (SOC)

PHYSICAL PROPERTIES	UNIT	RESULT	TEST METHOD
Flash Point (Min)	°C	240	ASTM D – 92
Pour Point (Max)	°C	24	ASTM D – 92
Density @ 15°C	KG/L	1.02	ASTM D – 1298
Kinematics Viscosity @ 15°C	cSt	40 – 50	ASTM D – 445
Aniline Point	°C	30	IP – 2
Sulfated ASH	%m	0.02	ASTM D – 2622
